

Amendments to the Claims:

The following listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently Amended) An insertion-molded cylindrical article, comprising
a cylindrical molded body including a sidewall portion having an inner surface
and an outer surface, defining an upper opening and a lower opening, and a mark produced by
injection of body forming material from an injection gate opening positioned on said inner
surface, and

a sheet-shaped insert having an upper edge and a lower edge;
wherein said insert is bonded to said outer surface of said sidewall portion, and
wherein said mark is positioned, as a result of the injection, at said inner
surface of the cylindrical molded body between said upper and lower edges of said insert so
as to be at a position corresponding to a position on said inner surface that is covered by said
insert, whereby said insert is bonded solely to said outer surface of said sidewall portion
substantially without wrinkles and without injected material on an outer surface of said insert.

2. (Previously Presented) The insertion-molded cylindrical article set forth in
claim 1, further comprising a gap on said outer surface positioned between opposed ends of
said insert and not covered by said insert,

wherein said mark of the injection gate opening is not located in said gap.

3. (Currently Amended) A method for making an insertion-molded cylindrical
article using an insertion injection molding mold,

said insertion-molded article comprising a cylindrical molded body having a
bottom portion, a sidewall portion having a molded body inner surface and a molded body
outer surface, and an insert having an upper edge and a lower edge;

said insertion injection molding mold comprising an outer mold unit having an inner surface and a pull-out mold unit and defining a core-inserting space therein, a core having an injection gate opening and shaped to be inserted and fitted into the outer molding unit, and a molding cavity defined between said outer mold unit and said core inside the injection molding mold,

said method ~~comprising~~comprising:

fitting, attaching and holding said insert along said inner surface of the outer molding unit in said molding cavity,

injecting a molten resin through said injection gate opening toward said molded body inner surface of the sidewall portion at a position between said upper and lower edges of the insert so as to be at a position corresponding to a position on said molded body inner surface that is covered by said insert so that an injection mark left by the injection gate is covered by the insert, and

curing and forming the cylindrical molded body while pushing the insert against the inner surface of the outer molding unit with the molten resin, the upper and lower end portions of the cylindrical molded body each defining an opening;

wherein said insert is solely bonded to said molded body outer surface of said sidewall portion of the cylindrical molded body substantially without wrinkles and without injected material on an outer surface of said insert.

4. (Previously Presented) The method set forth in claim 3, wherein said insertion-molded article further comprises a gap on said molded body outer surface of said sidewall portion positioned between opposed ends of said insert and not covered by said insert;

wherein the insert is fitted, attached and held along said inner surface of the molding cavity, and

wherein the molten resin is not injected toward said gap.

5. (Previously Presented) The method set forth in claim 3, wherein a knock-out pin is provided in the core, said method further comprising:

upwardly pulling out the pull-out mold unit of the outer mold unit after the insertion molding,

cutting a connection between the cured resin inside the injection gate opening and the cylindrical molded body by raising the knock-out pin, and

removing the cylindrical article from the core by pushing the bottom portion of the cylindrical molded body.

6. (Previously Presented) The method set forth in claim 3, wherein the insert is fitted, attached and held in a cylindrical shape along the inner surface of the outer mold unit in the molding cavity by applying a contact frictional force between the core and the insert, said contact frictional force formed by placing the insert into the outer mold unit while the core of the injection molding mold is pulled out from the outer mold unit and the molding cavity is opened, and forwardly moving the core into the outer mold unit.

7-11. (Canceled)

12. (Previously Presented) The method set forth in claim 4, wherein a knock-out pin is provided in the core, said method further comprising:

upwardly pulling out the pull-out mold unit of the outer core mold unit after the injection molding,

cutting a connection between the cured resin inside the injection gate opening and the cylindrical molded body by raising the knock-out pin, and

removing the cylindrical article from the core by pushing the bottom portion of the gate cylindrical molded body.

13. (Previously Presented) The method set forth in claim 4, wherein the insert is fitted, attached and held in a cylindrical shape along the inner surface of the outer mold unit in the molding cavity by applying a contact frictional force between the core and the insert, said contact frictional force formed by placing the insert in the cylindrical shape into the outer mold unit while the core of the injection molding mold is pulled out from the outer mold unit and the molding cavity is opened, and forwardly moving the core into the outer mold unit.

14. (Previously Presented) The method set forth in claim 5, wherein the insert is fitted, attached and held in a cylindrical shape along the inner surface of the outer mold unit in the molding cavity by applying a contact frictional force between the core and the insert, said contact frictional force formed by placing the insert in the cylindrical shape into the outer mold unit while the core of the injection molding mold is pulled out from the outer mold unit and the molding cavity is opened, and forwardly moving the core into the outer mold unit.

15-21. (Canceled)

22. (Previously Presented) The insertion-molded cylindrical article of claim 1, wherein said mark is positioned only at said inner surface of the sidewall portion while being closer to said upper edge than said lower edge of said insert in an axial direction of the cylindrical article and only at a position corresponding to a position on said inner surface that is covered by said insert.

23. (Previously Presented) The method set forth in claim 3, comprising injecting said molten resin through said injection gate opening toward said molded body inner surface only at a position closer to said upper edge than said lower edge of the insert in an axial direction of the cylindrical molded body and only at a position corresponding to a position on said cylindrical molded body inner surface that is covered by said insert.

24-25. (Canceled)

26. (New) The insertion-molded cylindrical article set forth in claim 1, wherein said insert is bonded to an entire surface of said outer surface of said sidewall portion, excluding a mouth portion of the cylindrical molded body.

27. (New) The method set forth in claim 3, wherein said insert is bonded to an entire surface of said outer surface of said sidewall portion, excluding a mouth portion of the cylindrical molded body.

28. (New) An insertion-molded cylindrical article made by an insertion injection molding mold,

said insertion-molded article comprising a cylindrical molded body having a bottom portion, a sidewall portion having a molded body inner surface and a molded body outer surface, upper and lower end portions, and an insert having an upper edge and a lower edge;

said insertion injection molding mold comprising an outer mold unit having an inner surface and a pull-out mold unit and defining a core-inserting space therein, a core having an injection gate opening and shaped to be inserted and fitted into the outer molding unit, and a molding cavity defined between said outer mold unit and said core inside the injection molding mold,

the article being made by a method comprising:

fitting, attaching and holding said insert along said inner surface of the outer molding unit in said molding cavity,

injecting a molten resin through said injection gate opening toward said molded body inner surface of the sidewall portion at a position between said upper and lower edges of the insert so as to be at a position corresponding to a position on said molded body inner surface that is covered by said insert so that an injection mark left by the injection gate is covered by the insert, and

curing and forming the cylindrical molded body while pushing the insert against the inner surface of the outer molding unit with the molten resin, the upper and lower end portions of the cylindrical molded body each defining an opening,

wherein said insert is solely bonded to said molded body outer surface of said sidewall portion of the cylindrical molded body substantially without wrinkles and without injected material on an outer surface of said insert.